

Typical Properties for SKYGREEN® J2003

• Injection Molded Property (ASTM Method)

| Property | Test Method | Unit | Typical Values |
|---|-------------|----------------------------|----------------------|
| Specific Gravity | ASTM D792 | - | 1.23 |
| Mold Shrinkage (Parallel to Flow) | ASTM D955 | % | 0.2~0.5 |
| Rockwell Hardness | ASTM D785 | R-scale | 105 |
| Mechanical | | | |
| Tensile Strength @ Yield 50mm/min (2 inch/min) | ASTM D638 | MPa (kgf/cm ²) | 45 (460) |
| Tensile Strength @ Break 50mm/min (2 inch/min) | ASTM D638 | MPa (kgf/cm ²) | 53 (540) |
| Elongation @ Yield 50mm/min (2 inch/min) | ASTM D638 | % | 5.0 |
| Elongation @ Break 50mm/min (2 inch/min) | ASTM D638 | % | 340 |
| Flexural Strength 1.27mm/min (0.05 inch/min) | ASTM D790 | MPa (kgf/cm ²) | 67 (680) |
| Flexural Modulus 1.27mm/min (0.05 inch/min) | ASTM D790 | MPa (kgf/cm ²) | 1800 (18300) |
| Izod Impact Strength, Notched @ 23 °C(73 °F) | ASTM D256 | J/m | No Break |
| Thermal | | | |
| Heat Distortion Temperature @ 0.455 MPa(66 psi) @ 1.820 MPa(66 psi) | ASTM D648 | °C (°F) | 74 (165) 64 (147) |
| Optical | | | |
| Haze | ASTM D1003 | % | < 1.0 |
| Transmittance | ASTM D1003 | % | 90 |
| Thermal properties (Flammability) | | | |
| UL Flammability Classification | | | |
| @ 1.0mm thickness | | | - |
| @ 1.5mm thickness | UL-94 | - | HB |
| @ 3.0mm thickness | | | V-2 |

The data listed here is preliminary data sheet of product. Therefore this sheet should not be used to establish specification limits or used alone as a basis for design. This information is not intended as a warranty of any kind. Customers must make their own representative test and assume all risks of use, whether used alone or in combination with other products. SK Chemicals assumes no obligation or liability of any advice furnished by it or results obtained with respect to these products. All warranties of merchantability for a particular purpose or use are excluded and disclaimed.

Headquarter / R&D center

686 Sampyung-Dong, Bundang-Gu, Seongnam-Si,
Gyeonggi-Do, 463-400 Korea
TEL : +82-2-2008-2008 / FAX : +82-2-2008-2009

Ulsan Plant

600 Hwangseong-Dong, Nam-Gu,
Ulsan 680-160 KOREA
TEL : +82-52-256-0121 / FAX : +82-52-256-0652

The information in this data sheet is, to the best of our knowledge, true and accurate. The representations about the product are based upon test results achieved under laboratory practices supervised and controlled by SK chemicals corporation.